

## Multi-purpose homogeneous vinyl floorings with excellent value for money, for education, retail and commercial sectors

### SENSORIAL BENEFITS

- Directional pattern
- Classical designs

### FUNCTIONAL BENEFITS

- Wear class P\*
- Practical patterns
- Weldable formulation
- PUR surface treatment for easier initial maintenance\*\*

### ENVIRONMENTAL BENEFITS



- Recyclable
- Low VOC emissions

\*Except Vylon Plus: Class M  
\*\*Except Vylon Plus: factory pre-treated



Homogeneous vinyl flooring: requires only dry buffing to regenerate its original appearance throughout lifetime

**CONTRACT PLUS**  
**STANDARD PLUS**  
**VYLON PLUS**

TECHNICAL DATA	STANDARDS	Contract Plus	Standard Plus 2.0mm	Standard Plus 1.5mm	Vylon Plus
<b>Classification</b>					
Classification	ISO 10581 (EN 649) commercial industrial	Classes: 34 43	Classes: 34 43	Classes: 32 41	Classes: 34 43
UPEC Classification	UPEC Classification	—			U4 P3 E2/3 C2
	NF UPEC certificate (NF 189)	—			312-024.1
<b>Characteristics</b>					
Total thickness	ISO 24346 (EN 428)	2.00mm	2.00mm	1.5mm	2.00mm
Wear layer thickness	ISO 24340 (EN430)	3 150g/m <sup>2</sup>	3 300g/m <sup>2</sup>	2 475g/m <sup>2</sup>	3 700g/m <sup>2</sup>
Surface treatment	-	PUR			Factory pre-treated
Abrasion group	EN 660-2	Group P: ≤ 4.00mm <sup>3</sup>			Group M: ≤ 7.50mm <sup>3</sup>
<b>Technical performances</b>					
Residual indentation	Average measured value	0.04mm			
	ISO 24343-1 (EN 433) requirement	≤ 0.10mm			
Reaction to fire	EN 13501-1 EN ISO 9239-1 EN ISO 11925-2	B <sub>n</sub> s1 ≥ 8 kW/m <sup>2</sup> Pass			
Dimensional stability	ISO 23999 (EN 434)	Rolls: ≤ 0.40%	Rolls: ≤ 0.40% Tiles: ≤ 0.25%	Rolls: ≤ 0.40%	Rolls: ≤ 0.40% Tiles: ≤ 0.25%
Castor wheel test	ISO 4918 (EN 425)	Suitable			
Marine equipment	IMO FTPC Part 5 and 2 IMO Res. A653		—		
Static electrical charge	EN 1815	< 2kV			
Light fastness	EN ISO 105-B02	≥ 6			
Chemical resistance	ISO 846: Part C	Good resistance			
Fungi and bacteria resistance	ISO 26987 (EN 423)	Does not favour growth			
Clean room test	ASTM F51/00	—	Class A	Class A	—
Slip resistance	DIN 51130 EN 13893	R9 ≥ 0.3			
Thermal resistance Underfloor heating	EN 12667 / DIN 52612	0.01m <sup>2</sup> K/W Suitable - max. 27°C		Suitable - max. 27°C	0.01m <sup>2</sup> K/W Suitable - max. 27°C
Form of delivery	ISO 24341 (EN 426) ISO 24342 (EN 427)	Rolls: 231m x 2m	Rolls: 231m x 2m Tiles: 50 x 50cm	Rolls: 251m x 2m	Rolls: 201m x 2m Tiles: 61 x 61cm 30 x 30cm
Colours	EN 12667 / DIN 52612	24	30 (rolls) 10 (tiles)	12	18

The above information is subject to modifications for the benefit of further improvement (01/2014).  
For more detailed technical information, please contact Tarkett.



Download the product offer